

Origineel Chapel Parket

Wood gradings



Premier



Allowed

- Knots up to 15 mm
- Cracks up to 20 mm
- Shade variations
- Occasional healthy sapwood*

Not allowed

- End cracks
- Insect damage
- Central core
- Ingrown bark
- Growth defects
- Mechanical damage

Rustic A



Allowed

- Open knots filled with filler up to a maximum of 40 mm
- Surface cracks up to a maximum of 50 mm
- Shade variations
- Sapwood up to a maximum of 15 mm wide*
- End cracks up to a maximum of 50 mm

Not allowed

- Insect damage
- Ingrown bark
- Central core
- Growth defects
- Mechanical damage

Rustic A/B Mix



Allowed

- combination with \pm 50% Rustic A and 50% Rustic B

Not allowed

Rustic B



Allowed

- Open knots filled with filler up to a maximum of 80 mm
- Filled open damage up to 60 mm
- Surface cracks up to a maximum of 400 mm
- Sapwood up to a maximum of 25 mm wide*
- Central core
- Growth defects up to a maximum of 30 mm
- Shade variations
- End cracks up to a maximum of 150 mm
- Ingrown bark up to a maximum of 40 mm

Not allowed

- Insect damage
- Mechanical damage

* Processes that alter the color of wood do not affect the sapwood of oak, nor do they change its color. When choosing modified floors in dark shades, especially those with darker tones, keep in mind that the sapwood portions of the wood will remain lighter.

3% of a given floor in another selection is allowed.